


Double-Coated Foam Tape



Liner:	96lb polycoated bleached kraft, silicone treated on both sides
LS Adhesive:	Non-sensitizing acrylic (M109)
Backing/Carrier:	1/16" white, crosslinked polyethylene foam
AS Adhesive:	Non-sensitizing acrylic (M109)

Applications

- Electrodes: ECG, EKG, TENS
- Medical device assembly
- Medical device attachment

Features

- Foam Carrier
- Non-Sensitizing Acrylic Adhesive
- 96lb Release Liner

Benefits

- Soft and flexible for maximum patient comfort
- Conformable and easily adapts to medical devices and body contours
- High tack and good shear strength
- Stable to EtO and gamma sterilization
- Easy to die-cut and process
- Good dimensional stability and lay flat

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness w/liner	72.3 mils	1.836 mm	PSTC 133
Adhesive Thickness (Air Side)	1.4 mils	0.036 mm	PSTC 133
Adhesive Thickness (Liner Side)	1.4 mils	0.036 mm	PSTC 133
Carrier Thickness	62.5 mils	1.588 mm	PSTC 133
Liner Thickness	7.0 mils	0.178 mm	PSTC 133
Adhesion to Steel (Air Side)	200 oz/in	21.88 N/cm	PSTC 101 Mod
Adhesion to Steel (Liner Side)	200 oz/in	21.88 N/cm	PSTC 101 Mod

Product Safety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic, non-sensitizing, and non-irritating.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.