


Double-Coated Tissue-Supported Tape



Liner: 60# Silicone-Coated Densified Kraft

Liner Side Adhesive: Rubber (I915)

Backing/Carrier: Tissue

Air Side Adhesive: Rubber (I915)

Applications

- Bonding and laminating to cloth, cork, paper, rigid and flexible plastics
- Splicing textiles, paper, and plastics
- Mounting displays, signs, posters, mirrors, nameplates, and decorative wall products
- Core starter tape

Features

- Rubber Adhesive
- Tissue Carrier
- 60# Kraft Liner

Benefits

- High tack
- Moderate shear strength
- Conformable and lightweight
- Easy tear
- Easily die-cut

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Overall Thickness (w/liner)	7.3 mils	0.185 mm	PSTC 133
Adhesive Thickness (Air Side)	1.30 mils	0.033 mm	PSTC 133
Carrier Thickness	1.2 mils	0.030 mm	PSTC 133
Adhesive Thickness (Liner Side)	1.30 mils	0.033 mm	PSTC 133
Liner Thickness	3.5 mils	0.089 mm	PSTC 133
Adhesion to Steel (Air Side)	98 oz/in	10.72 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel (Liner Side)	95 oz/in	10.39 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel (Air Side)	170 oz/in	18.60 N/cm	PSTC 101 Mod - 2 mil Alu Foil
Adhesion to Steel (Liner Side)	158 oz/in	17.29 N/cm	PSTC 101 Mod - 2 mil Alu Foil
Shear Strength	7 Days		PSTC 107 Mod
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	30 to 150 °F	-1 to 66 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.